



DPM

Digital Print Media

Roseash Limited
F, Fieldway, Greenford
Middlesex UB6 8UN

020 3264 1000
sales@dpm.com
www.dpm.com

SPECIFICATION SHEET

FRONTLIT MATT LAMINATED 340GSM (500Dx25D, 18 x 12)

Properties	Test Item	Unit	Result
Transmittance	ASTM E 424 6.5.2	%	13.7
Tensile Strength	ISO 13934-1:1999 C.R.E. Cut Strip Method	KGF/5CM	L: 90.1 W:89.3
Tearing Strength	ISO 13937-2:2000 C.R.E. Single Tear Method	KGF	L: 7.1 W: 5.0
Elongation	ISO 13934-2:2000 C.R.E. Cut Strip Method	%	L:14.9 W:31.2
Adhesion Strength	ISO 2411.C.R.E.	KGF/5CM	13.2
Flexing Endurance at Low Temp.	DIN53351	CYCLES	17000
Resistance to Low Temp.	DIN53351		-20°C
Resistance to High Temp.	DIN53351		80°C
Resistance to Weathering	ASTM G26, Xenon Arclamp, 18min spray/2hrs., 100 hrs, exposure		NO CHANGE
Practice for operating light-exp. With and without water	ASTM G26, Method A, Type B, Weather-O-Meter	GRADE	4
Determination Resistance of Synthetic Polymeric Materials to Fungi	ASTM G21-1996		0

Specification details are offered in good faith, but will not be accepted in matters of warranty