



# DPM

Digital Print Media

**Roseash Limited**  
F, Fieldway, Greenford  
Middlesex UB6 8UN

020 3264 1000  
sales@dpm.com  
[www.dpm.com](http://www.dpm.com)

## SPECIFICATION SHEET

### MESH 9OZ

#### (1000Dx1000D, 12 x 12 305 GSM/SM)

Properties	Test Item	Unit	Result
Transmittance	ASTM E 424 6.5.2	%	
Tensile Strength	ISO 13934-1:1999 C.R.E. Cut Strip Method	KGF/5CM	L: 195.5 W:164.5
Tearing Strength	ISO 13937-2:2000 C.R.E. Single Tear Method	KGF	L: 36.8 W: 27.9
Elongation	ISO 13934-2:2000 C.R.E. Cut Strip Method	%	L:23 W:21
Adhesion Strength	ISO 2411.C.R.E.	KGF/5CM	13.7
Flexing Endurance at Low Temp.	DIN53351	CYCLES	16000
Resistance to Low Temp.	DIN53351		-20°C
Resistance to High Temp.	DIN53351		80°C
Resistance to Weathering	ASTM G26, Xenon Arclamp, 18min spray/2hrs., 100 hrs, exposure		NO CHANGE
Practice for operating light-exp. With and without water	ASTM G26, Method A, Type B, Weather-O-Meter	GRADE	4
Determination Resistance of Synthetic Polymeric Materials to Fungi	ASTM G21-1996		0
Fire Rating	DIN 4102-1		B1

Specification details are offered in good faith, but will not be accepted in matters of warranty