



**DPM**

Digital Print Media

Roseash Limited  
F, Fieldway, Greenford  
Middlesex UB6 8UN

020 3264 1000  
sales@dpm.com  
www.dpm.com

## SPECIFICATION SHEET

### DOUBLE SIDED PVC 520GSM (250Dx500D/18 x 12)

Properties	Test Item	Unit	Result
Transmittance	ASTM E424 6.5.2	%	<0.1
Tensile Strength	ISO 13934-1:1999 C.R.E. Cut Strip Method	KGF/5CM	WARP: 78.5
Tearing Strength	ISO 13937-2:2000 C.R.E. Single Tear Method	KGF	WARP: 2.4 WEFT: 4.0
Elongation	ISO 13934-2:1999 C.R.E. Cut Strip Method	%	WARP: 39.9
Adhesion Strength	ISO 2411.C.R.E.	KGF/5CM	16.5
Flexing Endurance at Low Temp.	DIN53351	CYCLES	30
Resistance to Low Temp.	DIN53351 -20 °C , 5 HRS	%	WARP:99.4
Resistance to High Temp.	DIN53351 80 °C, 5 HRS	%	WARP: 98
Practice for operating light-exp.	ASTM G 26, Method A, Type B	GRADE	4
Determination Resistance of Synthetic Polymeric Materials to Fungi	ASTM G21-1996		0

Specification details are offered in good faith, but will not be accepted in matters of warranty