

# Vision Soft Coated Display



**dpm**  
digital print media

## Technical Data Sheet

### Vision Soft Coated Display

With INKTeX+BS® finishing for direct print, with flame retardant treatment,

Material	100 % Polyester			
Stock widths	Available up to 3.2m			
Finishing	rolled on paper cores			
Ecology	according to Öko-Tex Standard 100, product class IV			
Weight				
acc. to DIN EN 12127	220.00	[g/m <sup>2</sup> ]	+ - 3	[%]
Shrinkage				
Heat Shrinkage, 195 °C, 90 sec, lengthwise				
acc. to AA 25-02	-2.50	[%]	+ - 1	[%]
Heat Shrinkage, 195 °C, 90 sec, crosswise				
acc. to AA 25-02	-2.50	[%]	+ - 1	[%]
Tearing strength				
Elongation at 100 N, longitudinal direction				
acc. to DIN EN ISO 13934-1	18.50	[%]	+ - 20	[%]
Elongation at 100 N, cross direction				
acc. to DIN EN ISO 13934-1	5.00	[%]	+ - 20	[%]
Maximum tensile elongation, longitudinal direction				
acc. to DIN EN ISO 13934-1	75.00	[%]	+ - 20	[%]
Maximum tensile elongation, cross direction				
acc. to DIN EN ISO 13934-1	50.00	[%]	+ - 20	[%]
Maximum tearing strength, longitudinal direction				
acc. to DIN EN ISO 13934-1	min. 350.00	[N/5 cm]		
Maximum tearing strength, cross direction				
acc. to DIN EN ISO 13934-1	min. 1100.00	[N/5 cm]		



Digital Print Media, The Heights, Ibstone Road, Stokenchurch, Bucks, HP14 3BG  
T : 01494 760 240 E : sales@dpm.com W : www.dpm.com

# Vision Soft Coated Display



**dpm**  
digital print media

## Technical Data Sheet

### Vision Soft Coated Display

Continuing tearing strength, longitudinal direction

acc. to DIN EN ISO 13937-2

35.00 [N]

+ - 10 [%]

Continuing tearing strength, cross direction

acc. to DIN EN ISO 13937-2

20.00 [N]

+ - 10 [%]



Digital Print Media, The Heights, Ibstone Road, Stokenchurch, Bucks, HP14 3BG  
T : 01494 760 240 E : sales@dpm.com W : www.dpm.com