

Vision Eli-Decotex.

Technical Data Sheet

Material	100% Polyester with PU Blockout Coating	
Stock Widths	3100mm	
Weight acc. to DIN EN 12127	192gsm	+/- 3%
Shrinkage Heat Shrinkage, 195 °C, 90 sec, lengthwise acc. to AA 25-02	-3.00%	+/- 1%
Heat Shrinkage, 195 °C, 90 sec, crosswise acc. to AA 25-02	-3.00%	+/- 1%
Tearing Strength Elongation at 100 N, longitudinal direction acc. to DIN EN ISO 13934-1	28.00%	+/- 20%
Elongation at 100 N, cross direction acc. to DIN EN ISO 13934-1	62.00%	+/- 20%
Maximum tensile elongation, longitudinal direction acc. to DIN EN ISO 13934-1	95.00%	+/- 20%
Maximum tensile elongation, cross direction acc. to DIN EN ISO 13934-1	160.00%	+/- 20%
Maximum tearing strength, longitudinal direction acc. to DIN EN ISO 13934-1	min. 540.00 N/5cm	
Maximum tearing strength, cross direction acc. to DIN EN ISO 13934-1	min. 540.00 N/5cm	
Flame Retardancy	B1 / EN13501	