

Vision Recyclaflex Vestaweave.

Technical Data Sheet

Material	100% Recycled Polyester from post-consumer waste	
Stock Widths	3200mm	
Weight acc. to DIN EN 12127	115gsm	+/- 3%
Shrinkage Heat Shrinkage, 195 °C, 90 sec, lengthwise acc. to AA 25-02	max. - 2.00%	+/- 1%
Heat Shrinkage, 195 °C, 90 sec, crosswise acc. to AA 25-02	max. -2.00%	+/- 1%
Tearing Strength Maximum tensile elongation, longitudinal direction acc. to DIN EN ISO 13934-1	45.00%	+/- 20%
Maximum tensile elongation, cross direction acc. to DIN EN ISO 13934-1	45.00%	+/- 20%
Maximum tearing strength, longitudinal direction acc. to DIN EN ISO 13934-1	min. 250.00 N/5cm	+/- 20%
Maximum tearing strength, cross direction acc. to DIN EN ISO 13934-1	min. 260.00 N/5cm	+/- 20%
Air Permeability acc. to DIN EN ISO 9237	3900.00 l/m ² s	+/- 10%
Flame Retardancy	B1 / 13501	