

Vision Uniform Stretch Polyester.

Technical Data Sheet

Material	100% Polyester	
Stock Widths	2530mm / 3200mm	
Weight acc. to DIN EN 12127	215gsm	+/- 3%
Shrinkage Heat shrinkage, 195 degrees, 90sec, length acc. to DIN EN 12127	-2.00%	+/- 1%
Heat shrinkage, 195 degrees, 90sec, width acc. to DIN EN 12127	-2.00%	+/- 1%
Tearing Strength Elongation at 100 N, longitudinal direction acc. to DIN EN ISO 13934-1	63.00%	+/- 20%
Elongation at 100 N, cross direction acc. to DIN EN ISO 13934-1	7.00%	+/- 20%
Maximum tensile elongation, longitudinal direction acc. to DIN EN ISO 13934-1	86.00%	+/- 20%
Maximum tensile elongation, cross direction acc. to DIN EN ISO 13934-1	50.00%	+/- 20%
Maximum tearing strength, longitudinal direction acc. to DIN EN ISO 13934-1	min. 510.00 N/5cm	
Maximum tearing strength, cross direction acc. to DIN EN ISO 13934-1	min. 750.00 N/5cm	
Flame Retardancy	B1 / EN13501	