Vision Vestaweave.

Technical Data Sheet

Material	100% Polyester	
Stock Widths	2030mm / 3100mm	
Weight acc. to DIN EN 12127	115gsm	+/- 3%
Shrinkage Heat Shrinkage, 195 °C, 90 sec, lengthwise acc. to AA 25-02	max. - 2.00%	+/- 1%
Heat Shrinkage, 195 °C, 90 sec, crosswise acc. to AA 25-02	max. -2.00%	+/- 1%
Tearing Strength Maximum tensile elongation, longitudinal direction acc. to DIN EN ISO 13934-1	45.00%	+/- 20%
Maximum tensile elongation, cross direction acc. to DIN EN ISO 13934-1	45.00%	+/- 20%
Maximum tearing strength, longitudinal direction acc. to DIN EN ISO 13934-1	min. 250.00 N/5cm	+/- 20%
Maximum tearing strength, cross direction acc. to DIN EN ISO 13934-1	min. 260.00 N/5cm	+/- 20%
Air Permeability acc. to DIN EN ISO 9237	3900.00 l/m²s	+/- 10%
Flame Retardancy	B1 / 13501	

DPM
DIGITAL PRINT MEDIA

T: 01494 760240 **E:** sales@dpm.com **W:** www.dpm.com

DPM, Digital Print Media & Frieze Frames are trading names of Roseash Ltd. Registered in England 2920080, VAT GB 645 5703 29
Roseash Limited, Unit B The Height Business Centre, Ibstone Road, Stokenchurch, Buckinghamshire, HP14 3BG