

Vision Decostretch.

Technical Data Sheet

Material	88 % Polyester / 12 % Elasthan	
Stock Widths	3100mm	
Weight acc. to DIN EN 12127	180gsm	+/- 5%
Shrinkage Heat Shrinkage, 195 °C, 90 sec, lengthwise acc. to PA13	-3.50%	+/- 1%
Heat Shrinkage, 195 °C, 90 sec, crosswise acc. to AA PA13	-1.00%	+/- 1%
Tearing strength Elongation at 100 N, longitudinal direction acc. to DIN EN ISO 13934-1	106.00%	+/- 20%
Elongation at 100 N, cross direction acc. to DIN EN ISO 13934-1	86.00%	+/- 20%
Maximum tensile elongation, longitudinal direction acc. to DIN EN ISO 13934-1	167.00%	+/- 20%
Maximum tensile elongation, cross direction acc. to DIN EN ISO 13934-1	155.00%	+/- 20%
Maximum tearing strength, longitudinal direction (min.) acc. to DIN EN ISO 13934-1	min. 400.00 N/5cm	
Maximum tearing strength, cross direction (min.) acc. to DIN EN ISO 13934-1	min. 400.00 N/5cm	