

Vision Vestaweave Lite.

Technical Data Sheet

Material	100% Polyester	
Stock Widths	3100mm	
Weight acc. to DIN EN 12127	100gsm	+/- 5%
Air Permeability	4000.00 l/m ² s	+/- 10%
Tearing Strength		
Elongation at 100 N, longitudinal direction acc. to DIN EN ISO 13934-1	11.00%	+/- 20%
Elongation at 100 N, cross direction acc. to DIN EN ISO 13934-1	41.00%	+/- 20%
Maximum tensile elongation, longitudinal direction acc. to DIN EN ISO 13934-1	36.00%	+/- 20%
Maximum tensile elongation, cross direction acc. to DIN EN ISO 13934-1	66.00%	+/- 20%
Maximum tearing strength, longitudinal direction (min.) acc. to DIN EN ISO 13934-1	min. 240.00 N/5cm	
Maximum tearing strength, cross direction (min.) acc. to DIN EN ISO 13934-1	min. 240.00 N/5cm	
Continuing tearing strength, longitudinal direction acc. to DIN EN ISO 13937-2	12.00 N	+/- 10%
Continuing tearing strength, cross direction acc. to DIN EN ISO 13937-2	13.00 N	+/- 10%